



# Technical Data Sheet

Boulevard Series  
Adel Plant



| Product Name               | Swatch  | Size    | Standard  | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in <sup>2</sup> ) | Core Volume (%) |
|----------------------------|---|---------|-----------|--------------------------|------------------------------|----------------------------|---------------------------------|--------------------------|------------------------------------|-----------------|
| Autumn Haze                |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Cabernet Burgundy Velour   |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Cambridge Velour           |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Carbon Black Velour        |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Chelsea Ironspot           |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Hearthside Velour          |    | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Hearthside Velour Ironspot |   | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Red Desert Velour          |  | Modular | ASTM C216 | SW                       | FBS                          | >10,000                    | <6                              | <10                      | <10                                | <25             |
| Welsford Ironspot          |  | Modular | ASTM C216 | SW                       | FBX                          | >10,000                    | <6                              | <10                      | <10                                | <25             |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

| Size    | Width  | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|---------|--------|--------|--------|--------|----------------|-----------------|
| Modular | 3-5/8" | 2-1/4" | 7-5/8" | 4.0    | 525            | 6.86            |