

Technical Data Sheet

Industrial Rustic Series
Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Olde City		Standard	ASTM C216	SW	FBA	>5,000	<8	<10	<30	uncored
Olde England		Standard	ASTM C216	SW	FBA	>5,000	<8	<10	<30	uncored
Olde London		Standard	ASTM C216	SW	FBA	>5,000	<8	<10	<30	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024




Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Extruded Standard	3-5/8"	2-1/4"	8"	5.2	530	6.55

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

Technical Data Sheet

Industrial Rustic Series -- Thin Brick
Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Olde City Thin Brick		Standard	ASTM C1088	Exterior	TBA	N/A	<8	<10	N/A	N/A
Olde England Thin Brick		Standard	ASTM C1088	Exterior	TBA	N/A	<8	<10	N/A	N/A
Olde London Thin Brick		Standard	ASTM C1088	Exterior	TBA	N/A	<8	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots.
U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Thickness	Width	Height	Length	Weight	Brick per Pack	Brick per Pallet	Brick per Sq Ft
Standard Thin Brick Flat	3/4"	3/4"	2-1/4"	8"	1.1	30	2700	6.55
Standard Thin Brick Corner	3/4"	3-5/8"	2-1/4"	8"	1.4	12	1080	4.5/LF

Note: products are also available as Full Brick, see Full Brick Technical Data Sheet.