

# Technical Data Sheet

## Roman Maximus Series

Adel Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Black Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored
Columbia Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored
Flint Hills Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored
Flint Hills w/ Black Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored
Saddle Brown Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored
Sand Hills Red Roman Maximus		Roman Maximus	ASTM C216	SW	FBA	>15,000	<6	<10	<10	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Roman Maximus	3-5/8"	1-5/8"	23-5/8"	11.5	225	3.00