

TEST REPORT

Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile
12/06/2021

Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340	Plant:	Mid-Atlantic Plant
		Sampled Date:	12/01/2021
		Fired Date:	11/28/2021
Phone:	(p) (610) 562-3076		
Report Number:	GMAP598		
Description:	Shale Cut Thin Brick		

Absorption	1	2	3	4	5	Average
<i>24 Hour Cold Water (%)</i>	5.8	2.9	3.7	5	4	4.3
<i>5 Hour Boiling Water (%)</i>	7.5	4.6	5.4	6.6	5.6	5.9
<i>Saturation Coefficient</i>	0.78	0.62	0.68	0.76	0.71	0.71
Efflorescence	1	2	3	4	5	
<i>Efflorescence Detection</i>	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

C1088-20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale
Grade: Exterior - Interior



Mike Krzyzanowski
Technical Services Manager