

TEST REPORT

Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile
03/05/2020

Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340	Plant:	Sergeant Bluff Plant
Phone:	(p) (610) 562-3076	Sampled Date:	02/24/2020
Report Number:	GGSB-0009	Fired Date:	09/21/2020
Description:	Clay w/Additives Cut ThinBrick		

Absorption	1	2	3	4	5	Average
<i>24 Hour Cold Water (%)</i>	2.9	2.8	2.6	2.6	3.4	2.9
<i>5 Hour Boiling Water (%)</i>	3.1	2.9	2.8	2.8	3.7	3.1
<i>Saturation Coefficient</i>	0.93	0.94	0.93	0.91	0.9	0.92
Efflorescence	1	2	3	4	5	
<i>Efflorescence Detection</i>	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

C1088-20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale
Grade: Exterior - Interior



Mike Krzyzanowski
Technical Services Manager