

# Technical Data Sheet

Uptown Series  
Iberia Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Adrian		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Colonial Rose	Photo Coming Soon	Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>10,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Morning Dove		Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>10,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	<40
Ravenna		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Red Mahogany		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	<40
Rustic Sunset		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Shelby		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Sycamore		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40
Wyandot		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Queen	ASTM C652	SW	HBS	>5,000	<6	<10	<20	25-40

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-1/2"	2-1/4"	7-5/8"	3.6	525	6.86
Utility	3-1/2"	3-5/8"	11-5/8"	9.6	198	3.00
Queen	3	2-3/4"	7-5/8"	3.9	520	5.76