

Technical Data Sheet



Product Range	Product Name	Illustration	Swatch	Length (in)	Width (in)	Height (in)	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Average Unit Wt. (lb.)	Units per Square Foot	Pack Size	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Venetian Glass	Aqua Marine Frosted			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Aqua Marine Natural			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Aqua Marine Polished			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Aqua Marine Satin			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Arctic Crystal Frosted			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Arctic Crystal Natural			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Arctic Crystal Polished			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Arctic Crystal Satin			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Blue Sapphire Frosted			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Blue Sapphire Natural			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Blue Sapphire Polished			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Blue Sapphire Satin			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Golden Amber Frosted			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Golden Amber Natural			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Golden Amber Polished			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Golden Amber Satin			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Smokey Quartz Frosted			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Smokey Quartz Natural			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Smokey Quartz Polished			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored
Venetian Glass	Smokey Quartz Satin			7-5/8	3-5/8	2-1/4	ASTM C216*	SW	FBX	5.5	6.86	3	>5,000	0	0	0	uncored

*ASTM C216 grade and type only noted for comparison to other facing bricks, as Venetian Glass Brick is not a clay or shale unit, and therefore not subject to the ASTM C216 facing brick standard.

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.