














Technical Data Sheet

Boulevard Series
Adel Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Amherst Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Autumn Haze		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cabemet Burgundy Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cambridge Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Charleton Colonial		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Chelsea Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cordovan Bronze		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Hearthside Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Hearthside Velour Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Parkridge Velour		Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<10	<25
Red Desert Velour		Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<10	<25
Smoked Tudor Velour		Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<10	<25
Welsford Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.0	525	6.86