

Technical Data Sheet

Common Living Series
Marseilles Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Illini Commons		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
		Standard	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Illini Commons w/ Black		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
		Standard	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Marseilles Commons		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
		Standard	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	3.5	530	6.86
Standard	3-5/8"	2-1/4"	8"	3.7	530	6.55