

# Technical Data Sheet

EDL Paver Series  
Pittsburgh Plant



Product Name	Swatch	Size	Standard	Durability Class (Class)	Dimensional Variation (Application)	Abrasion Resistance (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	Abrasion Index
Brown Paver		4x8 Paver	ASTM C902	SX	PS	Type I	>10,000	<6	<10	<0.11
Cream Paver		4x8 Paver	ASTM C902	SX	PS	Type I	>15,000	<6	<10	<0.11
Dark Grey Paver		4x8 Paver	ASTM C902	SX	PS	Type I	>10,000	<6	<10	<0.11
Light Grey Paver		4x8 Paver	ASTM C902	SX	PS	Type I	>15,000	<6	<10	<0.11

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
4x8 Paver	4"	2-1/4"	8"	6.3	470	4.50