

Technical Data Sheet

Steel City Paver Series
Pittsburgh Plant



Product Name	Swatch	Size	Standard	Durability Class (Class)	Dimensional Variation (Application)	Abrasion Resistance (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	Abrasion Index
Steel City Paver		Modular	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8 Street	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8 Chamfer & Lug	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
Steel City Full Range Paver		Modular	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8 Street	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11
		4x8 Chamfer & Lug	ASTM C902	SX	PS	Type I	>10,000	<8	<10	<0.11

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular Paver	3-5/8"	2-1/4"	7-5/8"	5.9	525	4.50
4x8 Paver	4"	2-1/4"	8"	6.3	470	4.50
4x8 Street Paver	4"	2-3/4"	8"	7.6	380	4.50
4x8 Chamfer & Lug Paver	4"	2-1/4"	8"	6.3	470	4.50