

Technical Data Sheet

Symmetry Series
Pittsburgh Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Blacktone Smooth		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Braddock		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Duquesne		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Flashed Blacktone Smooth		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Golden Buff Smooth		Modular	ASTM C216	SW	FBX	>15,000	<6	<10	<10	<25
Shadow Gray Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-9/16"	2-1/4"	7-5/8"	4.1	525	6.86