

Technical Data Sheet

Symmetry Series
Pittsburgh Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|--------------------------|---|---------|-----------|--------------------------|------------------------------|----------------------------|---------------------------------|--------------------------|------------------------------------|-----------------|
| Blacktone Smooth |  | Modular | ASTM C216 | SW | FBX | >5,000 | <6 | <10 | <20 | <25 |
| Braddock |  | Modular | ASTM C216 | SW | FBX | >5,000 | <6 | <10 | <20 | <25 |
| Duquesne |  | Modular | ASTM C216 | SW | FBX | >5,000 | <6 | <10 | <20 | <25 |
| Flashed Blacktone Smooth |  | Modular | ASTM C216 | SW | FBX | >5,000 | <6 | <10 | <20 | <25 |
| Golden Buff Smooth |  | Modular | ASTM C216 | SW | FBX | >15,000 | <6 | <10 | <10 | <25 |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|---------|---------|--------|--------|--------|----------------|-----------------|
| Modular | 3-9/16" | 2-1/4" | 7-5/8" | 4.1 | 525 | 6.86 |