

Technical Data Sheet

True Gray Series
Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Cool Gray Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cool Gray Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
French Gray Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
French Gray Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Modern Gray Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Modern Gray Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Popular Gray Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Popular Gray Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.0	525	6.86