

Technical Data Sheet

Summit Series
Rocky Ridge Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
King William		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
Middle Plantation		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
Oyster Pointe		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
Royal Plum Full Range		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
Rustique		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
Sahara		Modular	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored
		Summit	ASTM C216	SW	FBS	>3,000	<14	<17	<60	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.1	500	6.86
Summit	3-5/8"	1-5/8"	17-5/8"	6.8	306	4.00